

Appl. No. 10/077,161  
Amdt. dated June 3, 2003  
Reply to Office Action of March 10, 2003

This listing of claims will replace all prior versions, and listings, of claims in the application:

**Listing of Claims:**

1. (Cancelled)
2. (Cancelled)
3. (Cancelled)
4. (Cancelled)
5. (Cancelled)
6. (Cancelled)
7. (Cancelled)
8. (Cancelled)
9. (Original) A tissue sheet having Wide Wales, a basis weight of from about 10 to about 35 grams per square meter (gsm) and one or more of the following pinhole-related indexes: a Pinhole Coverage Index of about 0.25 or less, a Pinhole Count Index of about 65 or less and a Pinhole Size Index of about 600 or less.

Appl. No. 10/077,161

Amdt. dated June 3, 2003

Reply to Office Action of March 10, 2003

10. (Original) The tissue sheet of claim 9 having a basis weight of from about 20 to about 35 gsm.
11. (Original) The tissue sheet of claim 9 having a basis weight of from about 20 to about 30 gsm.
12. (Original) The tissue sheet of claim 9 having a basis weight of from about 30 to about 35 gsm.
13. (Original) The tissue sheet of claim 9 having a Caliper of from about 700 to about 1500 microns.
14. (Original) The tissue sheet of claim 9 having a Caliper of from about 750 to about 1100 microns.
15. (Original) The tissue sheet of claim 9 having a ratio of the geometric mean modulus to the geometric mean tensile strength of about 5 kilometers or less per kilogram.
16. (Original) The tissue sheet of claim 9 having a ratio of the geometric mean modulus to the geometric mean tensile strength of from about 4 to about 5 kilometers per kilogram.
17. (Original) The tissue sheet of claim 9 having two outer layers and an inner layer, wherein the two outer layers contain primarily hardwood fibers and the inner layer contains primarily softwood fibers.

Appl. No. 10/077,161

Amdt. dated June 3, 2003

Reply to Office Action of March 10, 2003

18. (Original) A tissue sheet having Wide Wales and a geometric mean tensile strength of about 1200 grams or less per 7.62 centimeters, a basis weight of from about 10 to about 45 grams per square centimeter and one or more of the following pinhole-related indexes: a Pinhole Coverage Index of about 0.25 or less, a Pinhole Count Index of about 65 or less and a Pinhole Size Index of about 600 or less.
19. (Original) The tissue sheet of claim 18 wherein the basis weight is from about 10 to about 35 gsm.
20. (Original) The tissue sheet of claim 18 having a basis weight of from about 20 to about 35 gsm.
21. (Original) The tissue sheet of claim 18 having a basis weight of from about 20 to about 30 gsm.
22. (Original) The tissue sheet of claim 18 having a basis weight of from about 30 to about 35 gsm.
23. (Original) The tissue sheet of claim 18 having a geometric mean tensile strength of from about 500 to about 1200 grams.
24. (Original) The tissue sheet of claim 18 having a geometric mean tensile strength of from about 500 to about 1100 grams.
25. (Original) The tissue sheet of claim 18 having a geometric mean tensile strength of from about 800 to about 1000 grams.

Appl. No. 10/077,161

Amdt. dated June 3, 2003

Reply to Office Action of March 10, 2003

26. (Original) The tissue sheet of claim 18 having a Caliper of from about 700 to about 1500 microns.
27. (Original) The tissue sheet of claim 18 having a Caliper of from about 750 to about 1100 microns.
28. (Original) The tissue sheet of claim 18 having a ratio of the geometric mean modulus to the geometric mean tensile strength of about 5 kilometers or less per kilogram.
29. (Original) The tissue sheet of claim 18 having a ratio of the geometric mean modulus to the geometric mean tensile strength of from about 4 to about 5 kilometers per kilogram.
30. (Original) The tissue sheet of claim 18 having two outer layers and an inner layer, wherein the two outer layers contain primarily hardwood fibers and the inner layer contains primarily softwood fibers.
31. (Original) A tissue sheet having Wide Wales, a basis weight of from about 10 to about 35 grams per square meter (gsm) and a Pinhole Coverage Index of about 0.25 or less.
32. (Original) The tissue sheet of claim 31 wherein the Pinhole Coverage Index is about 0.20 or less.
33. (Original) The tissue sheet of claim 31 wherein the Pinhole Coverage Index is about 0.15 or less.
34. (Original) The tissue sheet of claim 31 wherein the Pinhole Coverage Index is from about 0.05 to about 0.15.

Appl. No. 10/077,161

Amdt. dated June 3, 2003

Reply to Office Action of March 10, 2003

35. (Original) A tissue sheet having Wide Wales and a geometric mean tensile strength of about 1200 grams or less per 7.62 centimeters, a basis weight of from about 10 to about 45 grams per square centimeter and a Pinhole Coverage Index of about 0.25 or less.
36. (Original) The tissue sheet of claim 35 wherein the Pinhole Coverage Index is about 0.20 or less.
37. (Original) The tissue sheet of claim 35 wherein the Pinhole Coverage Index is about 0.15 or less.
38. (Original) The tissue sheet of claim 35 wherein the Pinhole Coverage Index is from about 0.05 to about 0.15.